

## PATENT ABSTRACTS OF JAPAN

(11) Publication number:

2001-114813

(43) Date of publication of application: 24.04.2001

(51) Int. CI.

CO8F 4/654 CO8F297/08

(21) Application number : 11-297371

(71) Applicant: IDEMITSU PETROCHEM CO LTD

(22) Date of filing:

19. 10. 1999

(72) Inventor: SADASHIMA TAKANORI

KATAYAMA KIYOKAZU OBATA HIROSHI

OTA TAKESHI FUNABASHI HIDEO

(54) METHOD FOR PRODUCING PROPYLENE-BASED BLOCK COPOLYMER AND PROPYLENE-BASED BLOCK COPOLYMER

(57) Abstract:

PROBLEM TO BE SOLVED: To provide a method for producing a propylene-based block copolymer by which the molecular weight of the polypropylene component can easily be controlled by little hydrogen and a high-molecular weight ethylenepropylene copolymer component can be formed. SOLUTION: This propylene-based block copolymer is produced by using a polymerization catalyst for an olefin composed of (A) a preparatory polymerization catalyst ingredient prepared by bringing olefins into contact in the presence of (a) a solid catalyst ingredient obtained by bringing titanium tetrachloride and a magnesium compound into contact with a dialkyl phthalate, (b) an organometallic compound and (c) an organosilicon compound having Si-O-C bond. (B) the organometallic compound and (C) an organosilicon compound represented by general formula (1) (R1 denotes a 3-12C alicyclic

Si CH<sub>y</sub>-R<sup>2</sup> ... (1)

LEGAL STATUS


hydrocarbon).

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

hydrocarbon; R2 denotes a 3-200 branched hydrocarbon; and R3 denote a 1-200



[Date of final disposal for application]
[Patent number]
[Date of registration]
[Number of appeal against examiner's decision of rejection]
[Date of requesting appeal against examiner's decision of rejection]
[Date of extinction of right]

Copyright (C); 1998, 2000 Japan Patent Office